

MultiTrack SNW 14

MultiTrack SNW 14 Superior Nonwoven Geotextile, 1400N, 120g/m² - 4m x 100m roll



DESCRIPTION

MultiTrack SNW 14 Superior Nonwoven Geotextile, 1400N, 120g/m² - 4m x 100m roll

SPECIFICATION

General information

Stock code	GTSNW/14
Range	MultiTrack
Third party certified	CE UKCA
Geotextile product range	MultiTrack

Geotextile properties

Tensile strength (MD)	EN ISO 10319	8kN/m
Tensile strength (CMD)	EN ISO 10319	8kN/m
Elongation at max load (MD)	EN ISO 10319	45%
Elongation at max load (CMD)	EN ISO 10319	60%
Dynamic perforation resistance	EN ISO 13433	28mm
CBR puncture resistance	EN ISO 12236	1400N
Dynamic cone drop	EN ISO 13433	28mm
Water permeability	EN ISO 11058	110L/m ² .s

Characteristic opening size	EN ISO 12956	120µm
Thickness under 2kPa	EN ISO 9863-1	1.2mm
Weight	EN ISO 9864	120g/m ²

NOTES

Product may be subject to longer lead times, contact the Wrekin Geosynthetics team for details.

1. Geoworks (trading as Wrekin Products Ltd.) continually seeks to improve its products and, therefore, reserves the right to alter product specifications without prior notice.
2. It is the responsibility of all users to satisfy themselves the above data is current.
3. Installation details are available in the [knowledge base](#).
4. All Geoworks products are supplied subject to our [Terms and Conditions of Sale](#).

