


## E'GRID 3030L

E'GRID 3030L Premium Biaxial Geogrid Polypropylene, large aperture - 4m x 50m roll



CHARACTERISTIC	VALUE
Description	E'GRID 3030L Premium Biaxial Geogrid Polypropylene, large aperture - 4m x 50m roll

## SPECIFICATION

### GENERAL INFORMATION

Stock code	GGEGRID/30L
Range	E'GRID
Third party certified	CE UKCA
Roll sizes	4m x 50m
Geogrid product range	E'GRID

### GEOGRID PROPERTIES

Tensile strength (MD)	EN ISO 10319	30kN/m
Tensile strength (CMD)	EN ISO 10319	30kN/m
Tensile load (2% strain) (MD)	EN ISO 10319	12kN/m
Tensile load (2% CMD)	EN ISO 10319	12.5kN/m
Tensile load (5% strain) (MD)	EN ISO 10319	24kN/m
Tensile load (5% CMD)	EN ISO 10319	25kN/m
Aperture opening size		66mm x 66mm
Junction efficiency		95%
Radial stiffness		620kN/m

## NOTES

**Max. elongation:** 15% in MD, 13% in CMD

**Weight:** 63kg  $\pm$ 10%

[Network Rail Approved product with Certificate of Full Acceptance number PA05/05826.](#)

- ▶ All strength and load figures are based on test results from the manufacturer's laboratory, measured in accordance with ISO 10319 at the temperature of  $21\pm1^{\circ}\text{C}$  and calculated as a lowest 95% confidence limit in accordance with ISO 2602.
  - ▶ Measured by comparing the results of tests in accordance with test methods GRI/GG2 and GRI/GGI.
  - ▶ Radial stiffness measured at 2% strain under  $360^{\circ}$  radial loading. Determined from tests in accordance with EN ISO 10319.
  - ▶ Carbon Black content  $\geq 2\%$ .
  - ▶ Other roll sizes are available to order.
  - ▶ Other tensile strengths are available to order.
- 
- ▶ Geoworks (trading as Wrekin Products Ltd.) continually seeks to improve its products and, therefore, reserves the right to alter product specifications without prior notice.
  - ▶ It is the responsibility of all users to satisfy themselves the above data is current.
  - ▶ Installation details are available in the [knowledge base](#).
  - ▶ All Geoworks products are supplied subject to our [Terms and Conditions of Sale](#).