

## FasTrack 35/35

FasTrack 3535 Woven Geotextile, 3600N, 140g/m<sup>2</sup> - 5.25m x 100m roll



UK  
CA CE

### DESCRIPTION

FasTrack 3535 Woven Geotextile, 3600N, 140g/m<sup>2</sup> - 5.25m x 100m roll

## SPECIFICATION

### General information

Stock code	GTSG/FASTRACK/3535
Range	FasTrack
Third party certified	UKCA CE
Roll sizes	5.25m x 100m
Geotextile product range	FasTrack

### Geotextile properties

Material		Polypropylene
Tensile strength (MD)	EN ISO 10319	35kN/m
Tensile strength (CMD)	EN ISO 10319	35kN/m
Elongation at max load (MD)	EN ISO 10319	15%
Elongation at max load (CMD)	EN ISO 10319	14%
Static puncture resistance	EN ISO 12236	3.6kN
Dynamic perforation resistance	EN ISO 13433	16mm

<b>CBR puncture resistance</b>	EN ISO 12236	3600N
<b>Dynamic cone drop</b>	EN ISO 13433	16mm
<b>Water permeability</b>	EN ISO 11058	30L/m <sup>2</sup> .s
<b>Characteristic opening size</b>	EN ISO 12956	390µm
<b>Thickness under 2kPa</b>	EN ISO 9863-1	1mm
<b>Weight</b>	EN ISO 9864	140g/m <sup>2</sup>

1. Wrekin Products Ltd is continually seeking to improve our products and therefore reserves the right to alter product specifications without prior notice.
2. It is the responsibility of all users to satisfy themselves the above data is current.
3. Installation details are available on request.
4. All Wrekin products are supplied subject to our [Terms and Conditions of Sale](#)

